



## PAINT, TAR AND RUBBER REMOVER

for PAVERS AND SLABS

1 L • 20L

1 U.S. qt. • 5.25 U.S. gal.

### UPDATE

**May 12, 2004**

Make sure that you have an up-to-date technical data sheet at hand.

Canada and U.S.A.: dial 1-800-465-7325.

Others: dial 514-523-8324 (Canada).

[www.techniseal.com](http://www.techniseal.com)

### FUNCTION

Removes sealant, paint, tar or bitumen, rubber and chewing gum.

### APPLICATIONS

- Pavers and slabs made of concrete or natural stone, masonry, etc.
- Concrete, clay, stone, marble, granite, slate, etc.
- Driveways, pool decks, patios, terraces, commercial parking lots, pedestrian areas, buildings, etc.

### DESCRIPTION

TECHNI-SEAL PAINT, TAR AND RUBBER REMOVER FOR PAVERS AND SLABS effectively dissolves sealant, paint, tar or bitumen, rubber and chewing gum on pavers, slabs, concrete and masonry. Dibasic-ester-based, it works and evaporates slowly, making stripping of large surfaces much easier, especially when the ground is hot. Its emulsifying additives make it easy to rinse with a pressure washer.

**DIRECTIONS**

Read the Material Safety Data Sheet before using this product. Wear adequate protective clothing.

**Stains:** Surface should, ideally, be warm to the touch (morning). Cover stain generously with REMOVER; let work for 5 to 10 minutes. Reapply product and, using a SMALL TECHNI-SEAL BRUSH, scrub until stain is dissolved. Do not let dry; rinse immediately.

**NOTE:** This product dissolves any sealant; apply a new coat of sealant on stripped surface.

**Stripping of large surfaces:** Wear metal-studded shoes (golf). Start application at the bottom of the slope. Strip one 18-square metre section (200 sq. ft.) at a time. Apply a generous coat of REMOVER using a roller for rough surfaces. Let work for approximately 10 minutes, taking care not to let the product dry. If the REMOVER should dry, apply a new coat. For rinsing, it is very important to use a pressure washer (minimum flow: 8 gallons (36L)/min., pressure: 1,500 to 3,000 lb./sq. in. (680-1,360 kg/6.5 cm<sup>2</sup>), jet angle: 30 to 45°). Keeping the nozzle close to the surface (15 cm/6 in) and directing it towards the bottom of the hill, thoroughly rinse every square inch of the section going backwards, from the bottom to the top of the hill. Take care not to splash the part yet to be rinsed behind you, for water neutralizes the effect of REMOVER. Let dry. Repeat if necessary.

**CONSUMPTION**

0.7 to 1 litre per square metre.

0.7 to 1 quart per 10.75 sq. ft.

The quantity required depends on the porosity of the material to be treated. It is recommended that a small area be tested to determine the exact amount needed.

**PACKAGING**

**CANADA**

Product Code	Retail Size	Pro Size	Units per box	Units per pallet
141-541	1 L	•	6	720
241-547	•	20 L	•	48

**USA**

Product Code	Retail Size	Pro Size	Units per box	Units per pallet
121-541	1 qt.	•	6	720
221-547	•	5.25 gal.	•	48

**WARNINGS**

**CAUTION**

COMBUSTIBLE. MAY CAUSE IRRITATION

Keep away from heat and flame.

Avoid contact with eyes, skin and clothing.

Keep out of reach of children.

**Contains:** Aromatic petroleum solvent.

**SHIPPING**

**Land and Sea**

Not regulated

Packing Group : III  
 Flash Point : > 37.8°C (100°F)  
 Small means of containment : ≤ 454L (100 gal.)

**LIMITED WARRANTY:** Since it has no control over surface preparation and product application, Techni-Seal can not guarantee the results. Techni-Seal's warranty is limited to the replacement of product proven defective. Note: User should have an up-to-date technical data sheet handy and make sure that this product meets his or her needs by carrying out a test under anticipated conditions of use.